

WHAT IS CLAIMED IS:

- Sub B3/
1. A recording medium comprising a substrate having a glossy coating thereon, the glossy coating comprising alumina particles and a binder, wherein the alumina particles are aggregates of primary particles.
- Sub C2
2. The recording medium of claim 1, wherein the substrate comprises a polymer or cellulose paper.
3. The recording medium of claim 1, wherein the substrate comprises poly(ethylene terephthalate).
4. The recording medium of claim 1, wherein the alumina particles are fumed alumina particles.
- Sub A3/
5. The recording medium of claim 1, wherein the aggregates have a mean diameter of about 80-300 nm.
6. The recording medium of claim 1, wherein the aggregates have a surface area of about 20-400 m²/g.
- Sub B4/
7. The recording medium of claim 1, wherein the pigment to binder ratio is at least about 2:1 by weight.
8. A coating composition comprising alumina particles and a binder, wherein the alumina particles are aggregates of primary particles and the solids content of the alumina in the composition is at least about 10 wt.%.
9. The coating composition of claim 8, wherein the alumina particles are fumed alumina particles.
- Sub A4/
10. The coating composition of claim 8, wherein the aggregates have a mean diameter of about 80-300 nm.

00670110-0026600

11. The coating composition of claim 8, wherein the aggregates have a surface area of about 20-400 m²/g.

12. The coating composition of claim 8, wherein the pigment to binder ratio is at least about 2:1 by weight.

13. A method of preparing a coating composition, the method comprising:

providing a colloiddally stable dispersion comprising water and alumina particles, wherein the alumina particles are aggregates of primary particles and the solids content of the alumina particles in the dispersion is greater than about 20 wt.%;

adding a binder to and, optionally, diluting the colloiddally stable dispersion, until a desired pigment to binder ratio and overall solids content are obtained; and optionally adjusting the pH with a suitable acid or base.

14. The method of claim 13, wherein the alumina particles are fumed alumina particles.

15. The method of claim 13, wherein the aggregates have a mean diameter of about 80-300 nm.

16. The method of claim 13, wherein the aggregates have a surface area of about 20-400 m²/g.

17. The method of claim 13, wherein the pigment to binder ratio is at least about 2:1 by weight.

18. The method of claim 13, wherein the solids content of the alumina particles in the colloiddally stable dispersion is at least about 30 wt.%.

Sub
A5

19. The method of claim 13, wherein the zeta potential of the alumina particles in the colloiddally stable dispersion is at least about +20 mV.

5 20. The method of claim 13, wherein the pH of the colloiddally stable dispersion is about 3-5.

21. The method of claim 13, wherein the specific gravity of the colloiddally stable dispersion is about 1-2
10 kg/l.

22. The method of claim 13, wherein the apparent viscosity of the colloiddally stable dispersion is less than about 20 cp as measured in a Hercules® High-Shear
15 Viscometer at 4400 RPM, FF Bob measuring geometry.

23. The method of claim 13, wherein the viscosity of the colloiddally stable dispersion is less than about 100 cp as measured in a Brookfield Model RV viscometer,
20 spindle #1, after about 30 seconds at 60 RPM.

24. A coating composition prepared by the method of claim 13.

25 25. A method of preparing a recording medium, the method comprising:
providing a substrate;
coating the substrate with the coating composition of claim 8 to produce a substrate coated with a coating;
30 optionally calendering the coated substrate; and
drying the coated substrate.

26. A method of preparing a recording medium, the method comprising:
35 providing a substrate;

009260" 8TT02960

coating the substrate with the coating composition
of claim 24, to produce a substrate coated with a
coating;

5 optionally calendering the coated substrate; and
drying the coated substrate.

27. A recording medium prepared by the method of
claim 25.

10 28. A recording medium prepared by the method of
claim 26.

SUB
B5

ADD
B6

009260-8TTD